Barri del migdia S/N - E 08396 Sant Cebrià de Vallalta (Barcelona - Spain) sauleda@frenossauleda.com Tel. (+ 34) 93 763 11 20 Fax (+ 34) 93 763 10 61

ID Material: N 3 Rble: R. Antich Revision: 7

Last updated: 17/11/2022

MC3

MC3 is a rigid, semi-metallic, moulded material. It is composed of resins, and it uses rubber compound as a link system with friction modifier agents, mineral fibers and fine copper shavings to enhance its strength. It is a quick temperature disipating formulation from the operating surface. MC3 has a high and very stable friction coefficient, and excellent resistance to fading. MC3 is a fully cured material and is fully suitable for bonding & riveting.

Material data

Friction Properties (according graphics)		
Static Friction Coefficient (15bar, from box):	0.60±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.65±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
Tº Fading:	>400	°C
Physical properties		
Hardness (DIN53505):	88±5	Shore-D
Specific Gravity (ASTM D792):	2±0.10	gr/cm3

Mechanical properties

Thermal Conductivity (ASTM E1952):

Tensile Strength (ASTM D638):	15±1	N/mm²
Compressive Strength (ISO 844:2014):	126±5	N/mm²
Shear Modulus (ASTM D2344-00):	2154±100	N/mm²
Poisson Coefficient (ASTM D638):	0.23±0.03	
Young Modulus (ASTM D638):	5300±100	N/mm²

 0.31 ± 0.01

W/m°K

Recommended Working Values

T° Max. Continuous Operation:	400	°C
T° Max. Intermittent Operation:	500	°C

Material type: Rigid material

Appearance / Formats











Applications

Forging machinery - Heavy duty static applications - Heavy-duty industrial machinery - Machinery Mining industries - Punch-die press blocks - Ring segments

Price Level: € €

Reach (EC)1907/2023 - RoHS 2015/863/EU: Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

