

ID Material: 89 Rble: R. Antich Revision: 6

Last updated: 04/08/2021

Barri del migdia S/N - E 08396 Sant Cebrià de Vallalta (Barcelona - Spain) sauleda@frenossauleda.com Tel. (+ 34) 93 763 11 20 Fax (+ 34) 93 763 10 61

SA80/25

SA80/25 is a non-asbestos and moulded friction material. With a low friction coefficient and good resistance against wear. It is composed basically of resins as a link system with frictional modifier agents and mineral fibres to enhance its strength which helps to establish the friction coefficient value. It is black. It is a fully cured material and is suitable for both bonding and riveting.

Material data

Friction Properties (according graphics)		
Static Friction Coefficient (15bar, from box):	0.39±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.35±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
Tº Fading:	>250	°C
Physical properties		
Hardness (DIN53505):	70 - 75	Shore-D
Specific Gravity (ASTM D792):	1,65±0.05	gr/cm3
Ignition Loss (ASTM D7348):	34 - 38	%
Acetone Extraction (ASTM D494):	2±0.2	%
Mechanical properties		
Tensile Strength (ASTM D638):	16±5	N/mm²
Compressive Strength (ISO 844:2014):	100±5	N/mm²
Young Modulus (ASTM D638):	3800±100	N/mm²
Recommended Working Values		
T° Max. Continuous Operation:	200	°C
T° Max. Intermittent Operation:	250	°C

Material type: Rigid material

Appearance / Formats











Applications


Continuous brakes - Miscellaneous industrial brakes / clutches

Price Level: € €

Reach (EC)1907/2023 - RoHS 2015/863/EU: Compliance

Others

Perlitic cast iron, hardness Recommended Mating Surface: HB150-200 Recommended Adhesives: Thermosetting adhesive Oil Resistant:



Rubbing speed, temperature and pressure are related. Changing any values will change other. The values shown represent typical conditions, but are not ultimate limits of the material