

ID Material: 42  
Rble: R. Antich  
Revision: 1  
Last updated: 24/01/2019

# DD020

DD020 is a non-asbestos and moulded friction material. With a low friction coefficient and good resistance against wear. It is composed basically of resins as a link system with frictional modifier agents and mineral fibres to enhance its strength which helps to establish the friction coefficient value. It is black. It is a fully cured material and is suitable for both bonding and riveting.

## Material data

### Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.39±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.35±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>250	°C

### Physical properties

Hardness (DIN53505):	73±3	Shore-D
Specific Gravity (ASTM D792):	1.65±0.05	gr/cm3
Ignition Loss (ASTM D7348):	36±2	%
Acetone Extraction (ASTM D494):	2±0.2	%

### Mechanical properties

Tensile Strength (ASTM D638):	16±5	N/mm <sup>2</sup>
Compressive Strength (ISO 844:2014):	100±5	N/mm <sup>2</sup>

### Recommended Working Values

T° Max. Continuous Operation:	200	°C
T° Max. Intermittent Operation:	250	°C

Material type : Rigid material

### Appearance / Formats



### Applications





Continuous brakes - Friction Gasket - Friction washers - Micellaneous industrial brakes / clutches -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Yes

### Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes



Rubbing speed, temperature and pressure are related. Changing any values will change other. The values shown represent typical conditions, but are not ultimate limits of the material.