

ID Material: G5
Rble: R. Antich
Revision: 6
Last updated: 06/09/2019

AFV

AFV is a very strong rigid molded friction material. The basic compounds that have been used are resins for the bonding system, organic and minerals fibres and friction modifiers. AFV is suitable for industrial applications with a medium friction coefficient. It has good resistance to fading and wear. It is a fully cured material and is suitable for bonding and riveting.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.45±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.42±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T ^º Fading:	>350	°C

Physical properties

Hardness (DIN53505):	84±5	Shore-D
Specific Gravity (ASTM D792):	1.9±0.05	gr/cm ³
Ignition Loss (ASTM D7348):	31±2	%
Acetone Extraction (ASTM D494):	1±0.2	%

Mechanical properties


Tensile Strength (ASTM D638):	18±5	N/mm ²
Compressive Strength (ISO 844:2014):	140±5	N/mm ²
Shear Modulus (ASTM D2344-00):	2946±100	N/mm ²
Poisson Coefficient (ASTM D638):	0.195±0.03	
Young Modulus (ASTM D638):	7042±100	N/mm ²

Recommended Working Values

T ^º Max. Continuous Operation:	250	°C
T ^º Max. Intermittent Operation:	350	°C

Material type : Rigid material

Appearance / Formats



Applications

Brake pads - Heavy duty static applications - Holding Mechanical Structures
- Rings segments for machinery - Yaw brakes -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

