

ID Material: G5  
Rble: R. Antich  
Revision: 5  
Last updated: 22/06/2018

# AFV

**AFV is a very strong rigid molded friction material.** The basic compounds that have been used are resins for the bonding system, organic and minerals fibres and friction modifiers. AFV is suitable for industrial applications with a medium friction efficiency. It has good resistance to fading and wear. It is a fully cured material and is suitable for bonding and riveting.

## Material data

### Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.45±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.42±0.05	μ
Dynamic Friction Coefficient (10bar, 10m/s):	0.42±0.05	μ
Wear Rate (10bar, 15m/s):	50±10mm <sup>3</sup> /kwh	mm <sup>3</sup> /Kwh
T <sup>9</sup> Fading (10bar, 10m/s):	>350°C	°C

### Physical properties

Hardness (DIN53505):	84±5	Shore-D
Specific Gravity (ASTM D792-91):	1.9±0.05	gr/cm <sup>3</sup>
Ignition Loss (ASTM D-2524):	31±2	%
Acetone Extraction ISO2859-1:	1±0.2	%

### Mechanical properties


Tensile Strength (ASTM D638-10):	18±5	N/mm <sup>2</sup>
Compressive Strength (UNE 53205):	140±5	N/mm <sup>2</sup>
Poisson Coefficient:	0.195±0.03	
Young Modulus (ASTMD 638-10):	7042±100	N/mm <sup>2</sup>

### Recommended Working Values

T° Max. Continuous Operation:	250	°C
T° Max. Intermittent Operation:	350	°C

Material type : Rigid material

### Appearance / Formats



### Applications

Brake pads - Heavy duty static applications - Holding Mechanical Structures - Rings segments for machinery - Yaw brakes -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

### Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

