

ID Material: N 3
Rble: R. Antich
Revision: 5
Last updated: 14/06/2018

MC3

MC3 is a rigid, semi-metal, moulded material. It is composed of resins and rubber as a link system with friction modifier agents, mineral fibers and fine copper shavings to enhance its strength. Good friction value conducting heat from the operating surface. **It has a high and very stable friction coefficient and excellent resistance to fading.** MC3 is fully cured material and is suitable for bonding & rivetting.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.60±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.65±0.05	μ
Dynamic Friction Coefficient (10bar, 10m/s):	0.62±0.05	μ
Wear Rate (10bar, 15m/s):	100±10	mm ³ /Kwh
T ^o Fading (10bar, 10m/s):	>400°C	°C

Physical properties

Hardness (DIN53505):	88±5	Shore-D
Specific Gravity (ASTM D792-91):	2±0.05	gr/cm ³
Thermal Conductivity (ASTM E1952-01):	0.54±0.01	W/m ² K

Mechanical properties


Tensile Strength (ASTM D638-10):	15±1	N/mm ²
Compressive Strength (UNE 53205):	126±5	N/mm ²
Poisson Coefficient:	0.23±0.03	
Young Modulus (ASTMD 638-10):	5300±100	N/mm ²

Recommended Working Values

T ^o Max. Continuous Operation:	350	°C
T ^o Max. Intermittent Operation:	400	°C

Material type : Rigid material

Appearance / Formats



Applications

Forging machinery - Heavy duty static applications - Heavy-duty industrial machinery - Machinery Mining industries - Punch-die press blocks - Ring segments -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface: Perlitic cast iron, hardness HB150-200

Recommended Adhesives: Thermosetting adhesive

Oil Resistant: Yes

