

ID Material: 40
Rble: R. Antich
Revision: 6
Last updated: 28/01/2019

MM

MM is designed for heavy duty industrial brake applications. It consists a resin of impregnated textile based material with metal components. MM has a good mechanical resistance, is fully cured and suitable for bonding and riveting.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.45±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.50±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T ^º Fading:	>200	°C

Physical properties

Hardness (DIN53505):	90±5	Shore-D
Specific Gravity (ASTM D792):	1.6±0.05	gr/cm3
Ignition Loss (ASTM D7348):	20±2	%
Acetone Extraction (ASTM D494):	3±0.2	%

Mechanical properties


Tensile Strength (ASTM D638):	47±5	N/mm ²
Compressive Strength (ISO 844:2014):	410±5	N/mm ²
Poisson Coefficient (ASTM D638):	0.255	
Young Modulus (ASTM D638):	13354±100	N/mm ²

Recommended Working Values

T ^º Max. Continuous Operation:	200	°C
T ^º Max. Intermittent Operation:	250	°C

Material type : Rigid material

Appearance / Formats



Applications

Forging machinery - Heavy duty static applications - Heavy-duty industrial machinery - Holding Mechanical Structures - Machinery Mining industries -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

