

ID Material: 29
Rble: R. Antich
Revision: 6
Last updated: 07/07/2020

NT-DV

NT-DV is red molded friction material composed with fibres. **It has excellent mechanical characteristics, high compression strength and resistant to high temperatures.** Specially designed for hard working conditions. The material consists phenolic resins with a NBR bonding system, short fibres, friction modifiers and fillers. NT-DV is fully cured and suitable for bonding and riveting.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.55±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.59±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>350	°C

Physical properties

Hardness (DIN53505):	85±5	Shore-D
Specific Gravity (ASTM D792):	1.9±0.05	gr/cm3
Ignition Loss (ASTM D7348):	40±2	%
Thermal Conductivity (ASTM E1952):	0.27±0.1	W/m°K

Mechanical properties


Tensile Strength (ASTM D638):	30±5	N/mm ²
Compressive Strength (ISO 844:2014):	175±5	N/mm ²
Shear Modulus (ASTM D2344-00):	3390±100	N/mm ²
Poisson Coefficient (ASTM D638):	0.24±0.03	
Young Modulus (ASTM D638):	8400±100	N/mm ²

Recommended Working Values

T° Max. Continuous Operation:	300	°C
T° Max. Intermittent Operation:	400	°C

Material type : Rigid material

Appearance / Formats



Applications

Brake blocks - Forging machinery - Heavy duty static applications - Industrial clutches - Punch-die press blocks - Rings segments for machinery - Torque limitator -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

