

ID Material: i1  
Rble: R. Antich  
Revision: 7  
Last updated: 25/01/2019

# RWT

RWT is a grey metal based friction material which is able to perform at very high temperatures. It offers good heat dissipation and high compression strength characteristics. RWT is composed basically of resins as a link system, frictional modifier agents, mineral and organic fibres. It has a high and very stable friction coefficient with low rate of wear and excellent resistance to fading. It is fully cured and suitable for bonding and riveting.

## Material data

### Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.40±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.43±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>450	°C

### Physical properties

Hardness (DIN53505):	87±5	Shore-D
Specific Gravity (ASTM D792):	2.7±0.05	gr/cm3
Ignition Loss (ASTM D7348):	5±2	%
Acetone Extraction (ASTM D494):	1.5±0.2	%
Thermal Conductivity (ASTM E1952):	1.53±0.01	W/m°K

### Mechanical properties

Tensile Strength (ASTM D638):	35±5	N/mm <sup>2</sup>
Compressive Strength (ISO 844:2014):	185±5	N/mm <sup>2</sup>
Poisson Coefficient (ASTM D638):	0.22±0.03	
Young Modulus (ASTM D638):	16220±100	N/mm <sup>2</sup>

### Recommended Working Values

T° Max. Continuous Operation:	400	°C
T° Max. Intermittent Operation:	450	°C

Material type : Rigid material

### Appearance / Formats



### Applications

Brake pads - Heavy-duty industrial machinery - Industrial clutches - Machinery Mining industries - Rings segments for machinery - Rotor Brake -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

### Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

