

ID Material: 89  
Rble: R. Antich  
Revision: 5  
Last updated: 24/05/2018

# SA80/25

SA80/25 is a non-asbestos and moulded friction material. With a low friction coefficient and good resistance against wear. It is composed basically of resins as a link system with frictional modifier agents and mineral fibres to enhance its strength which helps to establish the friction coefficient value. It is black. It is a fully cured material and is suitable for both bonding and riveting.

## Material data

### Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.39±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.35±0.05	μ
Dynamic Friction Coefficient (10bar, 10m/s):	0.28±0.05	μ
Wear Rate (10bar, 15m/s):	25±10	mm <sup>3</sup> /Kwh
T <sup>o</sup> Fading (10bar, 10m/s):	>250°C	°C

### Physical properties

Hardness (DIN53505):	70 - 75	Shore-D
Specific Gravity (ASTM D792-91):	1,65±0.05	gr/cm <sup>3</sup>
Ignition Loss (ASTM D-2524):	34 - 38	%
Acetone Extraction ISO2859-1:	2±0.2	%

### Mechanical properties

Tensile Strength (ASTM D638-10):	16±5	N/mm <sup>2</sup>
Compressive Strength (UNE 53205):	100±5	N/mm <sup>2</sup>
Young Modulus (ASTMD 638-10):	3800±100	N/mm <sup>2</sup>

### Recommended Working Values

T <sup>o</sup> Max. Continuous Operation:	200	°C
T <sup>o</sup> Max. Intermittent Operation:	250	°C

Material type : Rigid material

### Appearance / Formats



### Applications

Continuous brakes - Miscellaneous industrial brakes / clutches -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

### Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

