

ID Material: N 3
Rble: R. Antich
Revision: 6
Last updated: 06/09/2019

CR-2M

CR-2M is a rigid, semi-metal, molded friction material. It is composed basically of resins and rubber as a link system with frictional modifier agents, mineral fibres and fine copper shavings to enhance its strength. They help to establish the friction value by conducting heat from the operating surface. It is black with copper shavings. It has a medium and very stable friction coefficient with low wear and excellent resistance to fading. CR-2M is fully cured material and is suitable for bonding and riveting.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.35±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.40±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>350	°C

Physical properties

Hardness (DIN53505):	80±5	Shore-D
Specific Gravity (ASTM D792):	2.10±0.05	gr/cm3
Thermal Conductivity (ASTM E1952):	0.54±0.01	W/m²K

Mechanical properties

Tensile Strength (ASTM D638):	15±5	N/mm²
Compressive Strength (ISO 844:2014):	126±5	N/mm²
Shear Modulus (ASTM D2344-00):	2170±100	N/mm²
Poisson Coefficient (ASTM D638):	0.24±0.03	
Young Modulus (ASTM D638):	5381±100	N/mm²

Recommended Working Values

T° Max. Continuous Operation:	350	°C
T° Max. Intermittent Operation:	400	°C

Material type : Rigid material

Appearance / Formats



Applications

Forging machinery - Gear discs - Heavy-duty industrial machinery - Machinery Mining industries - Mining industries - Punch-die press blocks - Ring segments -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

