

ID Material: 96
Rble: R. Antich
Revision: 6
Last updated: 25/01/2019

ST-06

ST06 is developed for static applications, it is rigid and moulded friction material. Its most noted characteristics are hardness, mechanical strength and resistance to temperature. Its co efficiency is very high. It is composed basically of resins and rubber as a link system with friction modifying agents. The mineral fibres enhance the strength which helps to establish the friction value. ST06 is fully cured and suitable for bonding and riveting.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.40±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.43±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>350	°C

Physical properties

Hardness (DIN53505):	83±5	Shore-D
Specific Gravity (ASTM D792):	1.80±0.05	gr/cm3

Mechanical properties


Tensile Strength (ASTM D638):	23±5	N/mm ²
Compressive Strength (ISO 844:2014):	120±5	N/mm ²
Poisson Coefficient (ASTM D638):	0.24±0.03	
Young Modulus (ASTM D638):	9190±100	N/mm ²

Recommended Working Values

T° Max. Continuous Operation:	250	°C
T° Max. Intermittent Operation:	350	°C

Material type : Rigid material

Appearance / Formats



Applications

Callipers for industrial applications - Damper Technologies - Forging machinery - Heavy duty static applications - Holding Mechanical Structures - Punch-die press blocks - Static brakes - Yaw brakes -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface: Perlitic cast iron, hardness HB150-200

Recommended Adhesives: Thermosetting adhesive

