

ID Material: 94
Rble: R. Antich
Revision: 6
Last updated: 28/01/2019

V2000R

V2000R is based on G95, this material has been developed in order to satisfy the demands of high temperature applications. The resin friction formula has been modified in such way to reduce its organic content. V2000R will resist higher operating temperatures than its predecessors whilst maintaining both frictional stability and low rate of wear. Also, the incorporation of a new specialist in yarn adds further merits in terms of physical strength to the facings, now with standing a 20% increase in rotational speed before burst. It is a rigid woven friction material with low organic content, this property helps to increase operation at high temperatures maintaining friction stability and low rate of wear.

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.50±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.46±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>350	°C

Physical properties

Hardness (DIN53505):	80±5	Shore-D
Specific Gravity (ASTM D792):	2.1±0.10	gr/cm3
Ignition Loss (ASTM D7348):	2±0.2	%
Acetone Extraction (ASTM D494):	30±2	%

Mechanical properties

Compressive Strength (ISO 844:2014):	120±5	N/mm ²
Burst Resistant (200 x 137 x 3,5) 200°C:	13500±100	RPM

Recommended Working Values

T° Max. Continuous Operation:	250	°C
T° Max. Intermittent Operation:	350	°C

Material type : Woven yarn

Appearance / Formats



Rings

Applications

Agricultural and bulding machinery - Industrial clutches - Torque limiter -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface: Perlitic cast iron, hardness HB150-200

Recommended Adhesives: Thermosetting adhesive

Oil Resistant: Yes

