

ID Material: 94  
Rble: R. Antich  
Revision: 5  
Last updated: 07/05/2018

# V2000R

V2000R is based on G95, this material has been developed in order to satisfy the demands of high temperature applications. The resin friction formula has been modified in such way to reduce its organic content. V2000R will resist higher operating temperatures than its predecessors whilst maintaining both frictional stability and low rate of wear. Also, the incorporation of a new specialist in yarn adds further merits in terms of physical strength to the facings, now with standing a 20% increase in rotational speed before burst. It is a rigid woven friction material with low organic content, this property helps to increase operation at high temperatures maintaining friction stability and low rate of wear.

## Material data

### Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.50±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.46±0.05	μ
Dynamic Friction Coefficient (10bar, 10m/s):	0.50±0.05	μ
Wear Rate (10bar, 15m/s):	100±10	mm <sup>3</sup> /Kwh
T° Fading (10bar, 10m/s):	>350°C	°C

### Physical properties

Hardness (DIN53505):	80±5	Shore-D
Specific Gravity (ASTM D792-91):	2.1±0.10	gr/cm <sup>3</sup>
Ignition Loss (ASTM D-2524):	2±0.2	%
Acetone Extraction ISO2859-1:	30±2	%

### Mechanical properties

Compressive Strength (UNE 53205):	120±5	N/mm <sup>2</sup>
Burst Resistant (200 x 137 x 3,5) 200°C:	13500±100	RPM

### Recommended Working Values

T° Max. Continuous Operation:	250	°C
T° Max. Intermittent Operation:	350	°C

Material type : Woven yarn

### Appearance / Formats



### Applications

Agricultural and bulding machinery - Industrial clutches - Torque limiter -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

### Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

